

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 1 035 600 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
13.09.2000 Bulletin 2000/37

(51) Int Cl.7: H01M 4/50, H01M 4/58

(21) Application number: 99402510.4

(22) Date of filing: 12.10.1999

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

- Kim, Geun-Bae
Cheonan-si, Chungcheongnam-do (KR)
- Park, Dong-Gon
Yongsan-ku, Seoul (KR)
- Noh, Hyung-Gon
Cheonan-si, Chungcheongnam-do (KR)

(30) Priority: 06.03.1999 KR 9907430

(71) Applicant: Samsung Display Devices Co., Ltd.
Suwon-Si, Kyungki-do (KR)

(74) Representative: Moncheny, Michel et al
c/o Cabinet Lavoix
2 Place d'Estienne d'Orves
75441 Paris Cedex 09 (FR)


(72) Inventors:
• Kweon, Ho-Jin
Cheonan-si, Chungcheongnam-do (KR)

(54) Positive active material for rechargeable lithium battery and method of preparing same

(57) A positive active material for rechargeable lithium batteries includes an active material component processed from a manganese-based compound. The transition metal compound is selected from Li_xMnO_2 , Li_xMnF_2 , Li_xMnS_2 , $\text{Li}_x\text{MnO}_{2-z}\text{F}_z$, $\text{Li}_x\text{MnO}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{F}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{S}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{F}_z$,

$\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_2\text{O}_4$, $\text{Li}_x\text{Mn}_2\text{F}_4$, $\text{Li}_x\text{Mn}_2\text{S}_4$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{F}_z$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{F}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{S}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{F}_z$, or $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{S}_z$ where $0 < x \leq 1.5$, $0.05 \leq y \leq 0.3$, $z \leq 1.0$ and M is selected from Al, Co, Cr, Mg, Fe or La. A metallic oxide is coated on the active material component.

FIG.1



Description

BACKGROUND OF THE INVENTION

(a) Field of the Invention

[0001] The present invention relates to a positive active material for rechargeable lithium batteries and a method of preparing the same and, more particularly, to a manganese-based positive active material for rechargeable lithium batteries which has a good cycle life characteristic.

(b) Description of the Related Art

[0002] Generally, manganese-based compounds such as LiMn_2O_4 and LiMnO_2 are the positive active material of choice for rechargeable lithium batteries because of their low cost, abundance and environmentally friendly characteristics. Among such manganese-based compounds, LiMn_2O_4 is particularly stable for the battery use and thus attractive for the electric vehicle application.

[0003] However, as compared to other lithiated transition metal oxides such as LiCoO_2 and LiNiO_2 , LiMn_2O_4 has a relatively low discharge capacity. Furthermore, when high rate of charge and discharge operations are cycled, the discharge capacity is excessively reduced. In particular, when the charge and discharge operations are continuously performed at high temperatures, manganese distributed in the surface of LiMn_2O_4 readily elutes to the electrolyte, causing a disproportionation reaction. This reaction seriously deteriorates the cycle life characteristic of the battery.

SUMMARY OF THE INVENTION

[0004] It is an object of the present invention to provide a manganese-based positive active material for rechargeable lithium batteries which exhibits a good cycle life characteristic at high temperatures.

[0005] This and other objects may be achieved by a positive active material for rechargeable lithium batteries including an active material component processed from a manganese-based compound. The manganese-based compound is selected from Li_xMnO_2 , Li_xMnF_2 , Li_xMnS_2 , $\text{Li}_x\text{MnO}_{2-z}\text{F}_z$, $\text{Li}_x\text{MnO}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{F}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{S}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{F}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_2\text{O}_4$, $\text{Li}_x\text{Mn}_2\text{F}_4$, $\text{Li}_x\text{Mn}_2\text{S}_4$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{F}_z$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{F}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{S}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{F}_z$, or $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{S}_z$ where $0 < x \leq 1.5$, $0.05 \leq y \leq 0.3$, $z \leq 1.0$ and M is selected from Al, Co, Cr, Mg, Fe or La. A metallic oxide is coated on the active material component.

[0006] A method of preparing the positive active material is performed by obtaining a powder from a source material. The source material is selected from Li_xMnO_2 , Li_xMnF_2 , Li_xMnS_2 , $\text{Li}_x\text{MnO}_{2-z}\text{F}_z$, $\text{Li}_x\text{MnO}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{F}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{S}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{F}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_2\text{O}_4$, $\text{Li}_x\text{Mn}_2\text{F}_4$, $\text{Li}_x\text{Mn}_2\text{S}_4$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{F}_z$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{F}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{S}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{F}_z$, or $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{S}_z$, where $0 < x \leq 1.5$, $0.05 \leq y \leq 0.3$, $z \leq 1.0$ and M is selected from Al, Co, Cr, Mg, Fe or La. The powder is then coated with a metallic alkoxide solution to make an alkoxide-coated powder. Thereafter, the metallic alkoxide-coated powder is heat-treated such that it is changed into a metallic oxide-coated powder.

M_yO_2 , $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{F}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{S}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{F}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_2\text{O}_4$, $\text{Li}_x\text{Mn}_2\text{F}_4$, $\text{Li}_x\text{Mn}_2\text{S}_4$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{F}_z$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{F}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{S}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{F}_z$, or $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{S}_z$, where $0 < x \leq 1.5$, $0.05 \leq y \leq 0.3$, $z \leq 1.0$ and M is selected from Al, Co, Cr, Mg, Fe or La. The powder is then coated with a metallic alkoxide solution to make an alkoxide-coated powder. Thereafter, the metallic alkoxide-coated powder is heat-treated such that it is changed into a metallic oxide-coated powder.

BRIEF DESCRIPTION OF THE DRAWINGS

[0007] A more complete appreciation of the invention, and many of the attendant advantages thereof, will be readily apparent as the same becomes better understood by reference to the following detailed description when considered in conjunction with the accompanying drawings, wherein:

Fig. 1 is a graph illustrating high-temperature charge and discharge characteristics of rechargeable lithium cells according to an example of the present invention and a comparative example;

Fig. 2 is a graph illustrating high-temperature cycle life characteristics of the rechargeable lithium cells of Fig. 1; and

Fig. 3 is a graph illustrating SIMS analysis results with respect to a rechargeable lithium cell according to another example of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

[0008] In a method of preparing a positive active material for rechargeable lithium batteries, a powder, being an active material precursor, is first processed from a manganese-based compound. The manganese-based compound is selected from Li_xMnO_2 , Li_xMnF_2 , Li_xMnS_2 , $\text{Li}_x\text{MnO}_{2-z}\text{F}_z$, $\text{Li}_x\text{MnO}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{F}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{S}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{F}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_2\text{O}_4$, $\text{Li}_x\text{Mn}_2\text{F}_4$, $\text{Li}_x\text{Mn}_2\text{S}_4$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{F}_z$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{F}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{S}_4$, $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{F}_z$, or $\text{Li}_x\text{Mn}_{2-y}\text{M}_y\text{O}_{4-z}\text{S}_z$, where $0 < x \leq 1.5$, $0.05 \leq y \leq 0.3$, $z \leq 1.0$ and M is selected from Al, Co, Cr, Mg, Fe or La. The powder processing step can be performed with a technique known in the related art.

[0009] Thereafter, the powder is coated with a metallic alkoxide solution. The metallic alkoxide solution is formed by the reaction of an alcohol with an alkali metal being 1 to 50 weight percent of the alcohol. The alkali metal may be preferably selected from Mg, Al, Co, K, Na, Ca, Si, Ti or Sr. More preferably, the alkali metal is selected from Si, Mg, Ti or Al. The alcohol is preferably selected from methanol or ethanol. When the alkali metal is less than 1 weight percent of the alcohol, the coating effect of the metallic alkoxide solution onto the powder is not induced. In contrast, when the alkali metal is more than 50 weight percent of the alcohol, the coating layer

of the metallic alkoxide solution becomes undesirably thick. A sputtering technique, a chemical vapor deposition (CVD) technique, a dip coating technique and other general-purpose coating techniques may be employed for the coating use. Among the techniques, the dip coating technique may be preferably used for coating the metallic alkoxide solution onto the powder.

[0010] The alkoxide-coated powder is then dried at 120°C for about 5 hours in an oven. The drying step is to uniformly distribute lithium salts in the powder. Thereafter, the dried powder is heat-treated at temperatures ranged from 200 to 1000°C for 1 to 20 hours under an oxidation atmosphere where dry air or oxygen is blowing. When the heat-treating temperature is lower than 200°C, the metallic alkoxide solution coated on the powder is not crystallized so that it prohibits free movement of lithium ions in the active material. It is preferable that the heat-treating step is performed at temperatures ranged from 300 to 900°C for 1 to 10 hours. This heat-treating operation makes the metallic alkoxide to be changed into a metallic oxide. In this way, a metallic oxide-coated active material is prepared.

[0011] The metallic oxide formed on the surface of the power may be derived from the single metallic alkoxide source or the composite sources of manganese of lithiated transition metal compound and metallic alkoxide. The thickness of the metallic oxide layer reaches up to 1 to 100nm and the quantity of metal content is ranged from 0.1 to 10 weight percent of the metallic oxide.

[0012] The following examples further illustrate the present invention.

Example 1

[0013] An aluminum isopropoxide solution having a 5 weight-percent concentration was prepared by refluxing an aluminum isopropoxide powder in ethanol at about 100°C for about half an hour. The aluminum isopropoxide solution was then mixed with a powder of $\text{Li}_x\text{Mn}_{2-y}\text{Al}_y\text{O}_{4-z}\text{F}_z$ where $0 < x \leq 1.5$, $0.05 \leq y \leq 0.3$ and $z \leq 1.0$ at an identical volume ratio in a moisture free dry room such that an overall surface of the power became wet sufficiently by the solution, and dried in the same room. Thereafter, the mixture was heat-treated at about 300°C for about 10 hours under a dry air atmosphere to thereby prepare a metallic oxide-coated active material. Then, the active material was mixed with Super P carbon for a conductive agent, KF-1300 polyvinylidene fluoride for a binder and N-methylpyrrolidone for a solvent to prepare an active material slurry. The slurry is cast into a tape shape to act as a positive electrode. The positive electrode is then assembled with a lithium metal foil for an opposite pole by using a lithium salt solution for an electrolyte to thereby fabricate a coin cell-type half cell. The lithium salt solution contained 1:1 volume ratio of ethylene carbonate and dimethyl carbonate for a solvent and LiPF_6 for a solute.

Example 2

[0014] The positive electrode preparing procedure was performed in the same way as in Example 1 with the exception that the heat-treating temperature was heightened up to 900°C. A coin-type half cell was fabricated with the resulting positive electrode in combination with other components as described in Example 1.

Example 3

[0015] An aluminum isopropoxide solution having a 5 weight-percent concentration was prepared by refluxing an aluminum isopropoxide powder in ethanol at about 100°C for about half an hour. The aluminum isopropoxide solution was then mixed with a powder of $\text{Li}_x\text{Mn}_2\text{O}_4$ where $0 < x \leq 1.5$ at an identical volume ratio in a moisture free dry room such that an overall surface of the power became wet sufficiently by the solution, and dried in the same room. Thereafter, the mixture was heat-treated at about 300°C for about 10 hours under a dry air atmosphere to thereby prepare a metallic oxide-coated active material. The subsequent positive electrode processing steps were performed in the same way as in Example 1. A coin-type half cell was fabricated with the resulting positive electrode in combination with other components as described in Example 1.

Comparative Example 1

[0016] The positive electrode preparing procedure was performed in the same way as in Example 1 with the exception that $\text{Li}_x\text{Mn}_{2-y}\text{Al}_y\text{O}_{4-z}\text{F}_z$ was directly used for the active material without the metallic-alkoxide coating operation. A coin-type half cell was fabricated with the resulting positive electrode in combination with other components as described in Example 1.

[0017] The coin type cells fabricated according to Example 1 and Comparative Example 1 were charged and discharged at 50°C from 0.1C to 1C rate over the voltage window between 4.3V and 3.0V. The charge and discharge characteristics of the cells in the early cycles were illustrated in Fig. 1. Further, the cycle life characteristics of the cells were illustrated in Fig. 2. In each of the figures, the charge and discharge characteristic of the cell according to Example 1 is indicated by a parenthesized alphabetic symbol "(a)" and that of the cell according to Comparative Example 1 is indicated by another symbol "(b)". As shown in Figs. 1 and 2, the cell according to Example 1 exhibited a slightly lower specific capacity but a better cycle life characteristic at high temperatures than the cell according to Comparative Example 1. It is presumed that the good cycle life characteristic of the cell is resulted because the metallic oxide layer coated on the surface of the manganese-based active material component prevents elution of manganese to the electrolyte. The cells fabricated according to Examples 2 and 3 also exhibited the desired perform-

ance characteristic similar to that of Example 1.

[0018] Meanwhile, a secondary ion mass spectrometry (SIMS) analysis was performed with respect to the positive active material prepared according to Example 3 to measure the component distribution ratio. The result was illustrated in Fig. 3. In the figure, the relative intensity of the aluminum component is indicated by a parenthesized alphabetic symbol "(a)" and that of the manganese component is indicated by another symbol "(b)". As shown in Fig. 3, it could be known that the aluminum component existed more in the surface portion of the active material and the manganese component existed more in the center portion of the active material. This proved that the overall surface of $\text{Li}_x\text{Mn}_2\text{O}_4$ was completely coated with aluminum oxide.

[0019] As described above, the positive active material for rechargeable lithium batteries has a good high-temperature cycle life characteristic.

[0020] While the present invention has been described in detail with reference to the preferred embodiments, those skilled in the art will appreciate that various modifications and substitutions can be made thereto without departing from the spirit and scope of the present invention as set forth in the appended claims.

Claims

1. A positive active material for rechargeable lithium batteries, the positive active material comprising:
 - an active material component processed from a manganese-based compound, the manganese-based compound being selected from the group consisting of Li_xMnO_2 , Li_xMnF_2 , Li_xMnS_2 , $\text{Li}_x\text{MnO}_{2-z}\text{F}_z$, $\text{Li}_x\text{MnO}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{F}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{S}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{F}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_2\text{O}_4$, $\text{Li}_x\text{Mn}_2\text{F}_4$, $\text{Li}_x\text{Mn}_2\text{S}_4$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{F}_z$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{S}_z$, $\text{Li}_x\text{Mn}_2\text{M}_y\text{O}_4$, $\text{Li}_x\text{Mn}_2\text{M}_y\text{F}_4$, $\text{Li}_x\text{Mn}_2\text{M}_y\text{S}_4$, $\text{Li}_x\text{Mn}_2\text{M}_y\text{O}_{4-z}\text{F}_z$, and $\text{Li}_x\text{Mn}_2\text{M}_y\text{O}_{4-z}\text{S}_z$ where $0 < x \leq 1.5$, $0.05 \leq y \leq 0.3$, $z \leq 1.0$ and M is selected from the group consisting of Al, Co, Cr, Mg, Fe and La; and
 - a metallic oxide coated on the active material component.
2. The positive active material of claim 1 wherein the metallic oxide has a metal component selected from the group consisting of Si, Mg, Ti and Al.
3. The positive active material of claim 1 or 2 wherein the metallic oxide has a thickness ranged from 1 to 100nm.
4. The positive active material of claim 2 or 3 wherein the metallic oxide has a 0.1 to 10 weight percent of metal component.
5. A method of preparing a positive active material for rechargeable lithium batteries, the method comprising the steps of:
 - obtaining a powder from a source material, the source material being selected from the group consisting of Li_xMnO_2 , Li_xMnF_2 , Li_xMnS_2 , $\text{Li}_x\text{MnO}_{2-z}\text{F}_z$, $\text{Li}_x\text{MnO}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{F}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{S}_2$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{F}_z$, $\text{Li}_x\text{Mn}_{1-y}\text{M}_y\text{O}_{2-z}\text{S}_z$, $\text{Li}_x\text{Mn}_2\text{O}_4$, $\text{Li}_x\text{Mn}_2\text{F}_4$, $\text{Li}_x\text{Mn}_2\text{S}_4$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{F}_z$, $\text{Li}_x\text{Mn}_2\text{O}_{4-z}\text{S}_z$, $\text{Li}_x\text{Mn}_2\text{M}_y\text{O}_4$, $\text{Li}_x\text{Mn}_2\text{M}_y\text{F}_4$, $\text{Li}_x\text{Mn}_2\text{M}_y\text{S}_4$, $\text{Li}_x\text{Mn}_2\text{M}_y\text{O}_{4-z}\text{F}_z$, and $\text{Li}_x\text{Mn}_2\text{M}_y\text{O}_{4-z}\text{S}_z$ where $0 < x \leq 1.5$, $0.05 \leq y \leq 0.3$, $z \leq 1.0$ and M is selected from the group consisting of Al, Co, Cr, Mg, Fe and La;
 - coating the powder with a metallic alkoxide solution to make an alkoxide-coated powder; and
 - heat-treating the metallic alkoxide-coated powder such that the metallic alkoxide-coated powder is changed into a metallic oxide-coated powder.
6. The method of claim 5 wherein the metallic alkoxide solution is selected from the group consisting of Si-alkoxide, Mg-alkoxide, Ti-alkoxide and Al-alkoxide.
7. The method of claim 5 or 6 wherein the metallic alkoxide solution contains a 1 to 50 weight percent of metal component.
8. The method of claims 5, 6 or 7 wherein the heat-treating step is performed at temperatures ranged from 200 to 1000°C for 1 to 20 hours.

FIG. 1




FIG. 2





FIG. 3





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 40 2510

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 789 410 A (MATSUSHITA ELECTRIC IND CO LTD) 13 August 1997 (1997-08-13) * claims 1,7 *	1,2	H01M4/50 H01M4/58
A	--- PATENT ABSTRACTS OF JAPAN vol. 011, no. 338 (E-553), 5 November 1987 (1987-11-05) & JP 62 119867 A (MATSUSHITA ELECTRIC IND CO LTD), 1 June 1987 (1987-06-01) * abstract *	1,5	
A	--- PATENT ABSTRACTS OF JAPAN vol. 1998, no. 03, 27 February 1998 (1998-02-27) & JP 09 293508 A (SONY CORP), 11 November 1997 (1997-11-11) * abstract *	1	
P,X	--- PATENT ABSTRACTS OF JAPAN vol. 1999, no. 08, 30 June 1999 (1999-06-30) & JP 11 071114 A (KAO CORP), 16 March 1999 (1999-03-16)	1,2	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
A	* abstract *	5	H01M
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 15 June 2000	Examiner Andrews, M
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03 82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 40 2510

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-06-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0789410 A	13-08-1997	JP 9213321 A	15-08-1997
		JP 9213322 A	15-08-1997
		JP 9245785 A	19-09-1997
		DE 69701411 D	20-04-2000
		US 5744266 A	28-04-1998
		US 5928714 A	27-07-1999
JP 62119867 A	01-06-1987	NONE	
JP 09293508 A	11-11-1997	NONE	
JP 11071114 A	16-03-1999	JP 2945377 B	06-09-1999

EPO FORM P0439

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82